

## 試驗報告



報告編號：HV-17-01588

頁數：4 OF 4

報告日期：2017年05月03日

### (2) 耐鹼性

實驗室環境條件：

環境溫度：23±2°C  
 相對濕度：65±5%RH

試驗方法：

參考 CNS 10757(1995) 塗料一般檢驗法(有關塗膜之物理、化學抗性之試驗法)

試驗條件：

試驗溶液：5% 氫氧化鈉  
 試驗溫度：23°C  
 試驗時間：24 小時

試驗結果：

試驗項目	試驗結果
耐鹼性	鹼浸漬試驗無異常

試驗照片：



----- 000 -----  
 This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.